

PIRELLI TIRE FACTORY - TURKEY

HPC® COATING



Hot Pipe Coating ® Thickness	Initial	Temp.	After	5 Days
Bare Pipe	207°C	404°F	210°C	410°F
3mm HPC (1/8") 125 mils DFT	158°C	316.4°F	150°C	302°F
7mm HPC (1/4") 250 mils DFT	112°C	233.6°F	102°C	215.6°F
10mm HPC (2/5") 394 mils DFT	78°C	172.4°F	68°C	68°C



Project Pictures courtesy of: Eric at Precoatings