



Accepted by National Institute of Standards and technology - No. 0252
Accepted by Canadian General Standards Board - No. 76005
ISO/IEC 25 Approved

March 5, 1999

Superior Products International P.O. Box 1930 Independence, MO 64055

Att: Mr. J.E. Pritchett President

DL-12111

OBJECTIVE

To test a coating for compliance to the requirements as outlined in ASTM E-1795, "Standard Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings", Type III, Either Exterior or Interior Use.

PRODUCT TESTED


RustGrip

TEST PROCEDURES

The coating was applied in two coats, 6 mils wet per coat with four hours dry between coats and allowed to cure twenty-one days at ambient conditions before testing in accordance with procedures outlined in ASTM E-1795.

TEST RESULTS

Test Results can be viewed in the **Appendix**





CONCLUSION

The sample of RustGrip conforms to all of the requirements in ASTM E 1795, Standard Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Buildings, Type III, Either Exterio or Interior Use, with the exception of flexibility after weathering and aging (paragraphs 5.9 and 5.10.2).

D/L Laboratories

CW


cc: S. Spindel

Mario Lazaro, Jr. Group Leader

* See pérest on mexit proper Pressed



116 East 16th Street New York, New York 10003-2112



Phone (212) 777-444 Fax (212) 505-841 E-mail: dllabs@aol.com

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252 Accepted by Canadian General Standards Board - No. 76005 - ISO/IEC 25 Approved

May 5, 1999

Superior Products P.O. Box 1930 Independence, MO 64055

Att: Mr. J.E. Pritchett

President

DL-12283

Via FAX (816) 241-1772

OBJECTIVE

To test a coating for compliance to the flexibility requirement as outlined in ASTM E 1795, "Standard Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Building", Type I: Interior Use Only, Par. 5.10.2, Aging - Interior Products.

PRODUCT TESTED

The coating was submitted by Superior Products and identified as RustGrip.

TEST PROCEDURE

The coating was applied at 3 mils wet film thickness and allowed to cure twenty-one days at ambient conditions before testing in accordance with procedures outlined in ASTM E-1795, Par. 10.10.2.

TEST RESULTS

The coating did not exhibit any cracking or other visual defects when measured at 0.25 inches from the end of the conical mandrel.

D/L Laboratories

CW

cc: T. Sliva S. Spindel

this project come the earlier of a com-





116 East 16th Street New York, New York 10003-2112 Phone (212) 777-444 Fax (212) 505-841 E-mail: dllabs@aol.co

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252
Accepted by Canadian General Standards Board - No. 76005 - ISO/IEC 25 Approved

July 21, 1999

Superior Products P.O. Box 1930 Independence, MO 64055

Att:

Mr. J.E. Pritchett President

DL-12370

Via FAX (816) 241-1772

OBJECTIVE

To test a coating for compliance to the flexibility requirement as outlined in ASTM E 1795, "Standard Specification for Non-Reinforced Liquid Coating Encapsulation Products for Leaded Paint in Building", Par. 5.10.1, Aging -Exterior Products.

PRODUCT TESTED

The coating was submitted by Superior Products and identified as RustGrip.

TEST PROCEDURE

The coating was applied at 3 mils wet film thickness and allowed to cure twenty-one days at ambient conditions before testing in accordance with procedures outlined in ASTM E-1795, Par. 10.10.1.

TEST RESULTS

The coating did not exhibit any cracking or other visual defects when measured at 0.25 inches from the apex of the conical mandrel.

D/L Laboratories

Mario Lazaro Jr

Group Leader

CW

cc: T. Sliva S. Spindel