



HPC®

Technical Data Sheet (10/11/18)

DESCRIPTION

HPC® Coating is designed to control heat transfer on surface temperatures up to 482°F (250°C). It is water-borne and extremely lightweight in appearance. HPC® Coating uses a special acrylic resin blend with specific ceramic compounds added to provide a non-conductive block against heat transfer.

HPC® Coating offers a “Green”, non-flammable, non-toxic formula for high heat surface applications over standard steam pipe or oven wall construction. HPC® Coating is easily applied using a texture sprayer, and can be applied over metal, concrete, wood, and other substrates.

If HPC® Coating is to be applied over flat steel surfaces, see manufacturer for instructions.

TYPICAL USES

- As an insulation system over hot pipes, tanks, and valves
- To block heat migration into cold tanks, lines, and valves
- As a system to block conductive and convective heat
- Easily applied when a hot system cannot be shut down

APPLICATION METHOD

HPC® Coating can be used for applications ‘up to’ 482°F (250°C). It must be applied according to Manufacturer’s Application Instructions.

NOTE: Applications applied over 482°F (250°C) may see the resins [turn tan](#) to brown in color next to the hot surface, but the HPC will continue to work as long as the ceramics are still in place.

HPC® Coating can be applied to metal, concrete, masonry and wood.

The application is applied using a texture sprayer. For specific instructions on surface preparation, mixing and application, please refer to the SPI Application Instruction sheet for HPC® Coating.

If HPC® Coating is applied on surfaces outdoors, you **must** overcoat the HPC with Super Therm®, Rust Grip®, SP Liquid Membrane or Enamo Grip according to what is needed. It cannot be left uncoated and left exposed to weather conditions. It is light-weight to insulate, which leaves it vulnerable to weather conditions.

HPC® Coating must be completely dry before applying top coat.

HPC® Multi-Mesh Membrane System is used on hot pipes when continuous cycles cause movement, and where continuous impact caused by workers handling the hot pipe is unavoidable. Apply Multi-Mesh Membrane between layers of RUST GRIP, ENAMO GRIP or MOIST METAL GRIP for exterior toughness. Multi-Mesh Membrane combined with RUST GRIP or MOIST METAL GRIP forms a hard cast for exterior strength and moisture barrier to protect the HPC system. A final top-coat of SP LIQUID MEMBRANE should be added for impact resistance and movement from elongation during heat cycles to avoid stress cracks.

NOTE: For surfaces over 482°F (250°C) see [Technical Sheet for HPC-HT \(high-temp version\)](#).

TESTS AND CERTIFICATIONS

1. ISO8302/ASTM C 177 – Thermal Conductivity (0.063 W/mK @ 86°F/30°C)
2. ISO 8302 – Thermal Conductivity
3. IMO – MSC.61(67) Smoke and Toxicity Test
4. Marine Approvals – American Bureau of Shipping;
5. USDA Approved
6. Russian field test – w/mK 0.035 avg.

MINIMUM SPREAD RATES (mil thickness)

- 22.4 sq. ft./gal = 50 mils dry film thickness
- 11.2 sq. ft./gal = 100 mils dry film thickness
- 5.61 sq. ft./gal = 200 mils dry film thickness
- 4.5 sq. ft./gal = 250 mils dry film thickness

PHYSICAL DATA

- ◆ Solids: By Weight: 49.0% / By Volume: 72.00%
- ◆ Dry Time: If between 200-300°F.; 10-30 minutes per coat, or until steaming action has finished.
- ◆ Water-borne
- ◆ Cures by evaporation
- ◆ Weight: 5.2 lbs. per gallon
- ◆ Vehicle Type: Acrylic Blend/Co-solvents
- ◆ Shelf Life: Up to 1 year if unopened under appropriate storage conditions (See MSDS)
- ◆ VOC Level: 25.1 grams/liter, 0.209 gal./lbs.
- ◆ pH: 8.5-9.5
- ◆ USDA Approved
- ◆ Maximum Surface Temperature when applying: 482°F (250°C)
- ◆ Minimum Surface Temperature when applying: 40°F (5°C)
- ◆ Maximum Surface Temperature after curing: 482°F (250°C)*
- ◆ HPC Coating will not totally burn. Any initial flame will burn off the surface resin before charring and blocking the flame.
- ◆ Operating temperatures have been higher in the field. See [manufacturer for instructions](#).

NOTE: Apply only over dry surfaces (inside or out) and when sun is shining (for external application). Do not apply on a full cloudy day with a chance for rain, or within 5° of dew point.

IMPORTANT

Do not take internally. Avoid contact with eyes. If solution does come in contact with eyes, flush immediately with water and contact a physician for medical advice. Avoid prolonged contact with skin or breathing of spray mist. **KEEP OUT OF REACH OF CHILDREN.**

LIMITATION OF LIABILITY: The information contained in this data sheet is based upon tests that we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by SPI, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge is reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and the end-user has the responsibility to determine the suitability of the product for its intended use.

SPI has no control over either the quality of condition of the substrate, or the many factors affecting the use and application of the product. Therefore, SPI does not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The information contained in this data sheet is subject to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and the user has the responsibility to ensure that this sheet is current prior to using the product.