

## BOMBARDIER (Katowice, Poland)

Done by **HTH-Novotech**.

Two hardening furnaces are insulated with 3 mm HSC®.

The temperatures before application: - on door 100 °C

- on the rest of the furnace 65 °C

The temperatures after application of 3mm HSC®: - on door 65 °C

- on the rest of the furnace 45 °C

As customer wanted it in silver/grey color we intended to use Rust Grip®, however in the light of your doubts we decided to apply over it a water-based paint.

Results you can see on the pictures.

