



Thermal
Fire
Corrosion

Call us for more information at 604-576-2212

NCFR 1000 - 1X TECHNICAL DATA SHEET

CHARACTERISTICS:

Finish.....Satin or Clear
Spreading Rate.....300 sq/ft per gallon
 in two (2) coats
Drying Time @75°F & 50% R.H.
 Between coats.....6-8 hours
 Before handling.....5 hours
 Finish should reach hardness in...48 hours
Shipping Weight..... .1 gallon – 10.8 lbs.
 5 gallon – 51.0 lbs
Weight/Gallon.....9.02 +/- 0.2 lbs.

Pacific Gravity.....1.096
Color....White, Clear, Custom Tinting available using
 universal colorants
Type of Cure..... Solvent Evaporation
Solids by weight..... 60% +/- 2%
Solids by Volume..... .45% +/- 2%
Reducer.....Xylene
Packaging..... 1 & 5 gallon containers
Shelf Life.....1 year Unopened
Clean up Solvent..... Xylene

SGS/US TESTING COMPANY FIRE HAZARD CLASSIFICATION

Class A rating when tested in accordance with ASTM-84, comparable to NFPA 255, UL 723 and UBC No. 8-1

Coating Detail	Classification or Rating (When Applied to Red Oak)	
	Flame Spread	Smoke Developed
NCFR 1000 – 1X applied in two Coats at 300 sq. ft./US gal.	25	60

NOTE: Red Oak was tested based on having one of the highest burn rates of most common wood types used in building assemblies.