



SPI COATINGS

PROVEN PERFORMANCE • REAL WORLD SOLUTIONS

SUNSHIELD

**INSULATION
AND
CORROSION
SPECIALISTS**

Technical Data Sheet (7/17/21)

DESCRIPTION

SUNSHIELD is a water-borne combination of high-performance duo of elastomeric acrylics and resin additives, which produces a tough, yet flexible coating film. It combines four different ceramics that provide both heat reflectivity and heat-blocking properties. SUNSHIELD is a flexible membrane with low permeability that can greatly reduce expansion and contraction of a roof. SUNSHIELD's blend of resin additives produce a flexible coating membrane that can be applied directly to any surface. It also prevents corrosion and surface deterioration. Although durable and offering solar blocking performance, SUNSHIELD does not give the same benefits as SUPER THERM®.

TYPICAL USES

- As a one-coat roofing insulation system on exteriors to block the migration of Solar Heat gain.
- As an insulation system for the exterior of vertical walls against Solar Heat.
- As insulation for transportation vehicles, refrigerated containers, reefer trucks, and railroad cars when applied to the exterior.
- As a "Green" coating where a low VOC and durability is needed (21 grams/ltr).
- As a system over metal, concrete, masonry, and wood to stop moisture penetration and corrosion.
- Ability to resist dirt, mold, mildew, and pollution to increase longevity, and reduce surface maintenance.
- As a topcoat over metal roofs, or an intermediate coat on flat roofs.

APPLICATION METHODS

SUNSHIELD can be applied to metal, concrete, masonry and wood. The application can be spray, brush or roller. For specific instructions on surface preparation, mixing and application, please refer to the SPI's application instructions for SUNSHIELD. This coating should never be applied at less than a total of 19 mils wet (450 microns), 10 mils dry (250 microns).

TESTS AND CERTIFICATIONS (partial list)

USDA Approved

FIELD TESTING has proven:

1. The coating provides a water-tight barrier
2. The coating can withstand large temperature variances without peeling, cracking or loss of adhesion
3. The coating is resistant to mold and mildew
4. Designed for flexibility and elongation, the coating is designed to move with the substrate, and to withstand the rigors of expansion and contraction
5. The ceramics contained have sound dampening qualities.

PHYSICAL DATA

- ◆ Solids: By weight 60% / By Volume: 54.9%
- ◆ 30-60 minutes to tack free at 70°F (21°C)
- ◆ Overcoat: 2 hours when 70°F (21°C) at 40% relative humidity
- ◆ Full Cure: 21 days
- ◆ Cures by evaporation
- ◆ Weight: 11.8 lbs. per gallon
- ◆ Vehicle Type: Acrylic blend
- ◆ Shelf Life: Up to 3 years if unopened under appropriate storage conditions (See MSDS).
- ◆ VOC Level: 21 grams/liter
- ◆ Viscosity: 105 – 110 KU;
- ◆ pH: 8.5-9.5
- ◆ Maximum Surface Temperature when applying: 150°F (65°C)
- ◆ Minimum Surface Temperature when applying: 40°F (5°C)
- ◆ Maximum Surface Temperature after curing: 300°F (149°C)

SPREAD RATE: 90 sq.ft./gallon; 10 dry mils

SAFETY PRECAUTIONS

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: proper ventilation, use of proper lamps, wearing of protective clothing and masks, tenting, and proper separation of application areas. For more specific safety procedures, please refer to the SUNSHIELD Material Safety Data Sheet. **KEEP OUT OF REACH OF CHILDREN.**

LIMITATION OF LIABILITY: The information contained in this data sheet is based upon tests that we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by SPI, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge is reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and the end-user has the responsibility to determine the suitability of the product for its intended use.

SPI has no control over either the quality of condition of the substrate, or the many factors affecting the use and application of the product. Therefore, SPI does not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

Information contained in this data sheet is subject to modification as a result of experience and continuous product development. This data sheet replaces and previous issues and the user has the responsibility to ensure that this sheet is current with the product.