

ASTM E 96 TESTING
(WATER METHOD)
FOR
SUPERIOR PRODUCTS
ON
ENAMO-GRIP
VTEC 100-2052
TESTED: OCTOBER 11 & 12, 2004



VTEC Laboratories Inc.

October 12, 2004

Client: Superior Products
10835 W 78th Street
Shawnee, KS 66214

Attention: J.E. Pritchett

Scope: This report contains the reference to the test method, preparation and conditioning of sample, observation of material, test and post test observation data test results.

Test Method: This test was conducted in accordance with ASTM E 96 specification.

This test method covers the determination of water vapor transmission (WVT) of materials through which passage of water vapor may be of importance. In the Water Method, the test specimen was sealed to the top of the cup containing distilled water and then placed in a test chamber at 90°F with a relative humidity of 50% for 24 hours. The cups were weighed at the beginning and at the end of the 24-hour cycle to determine how much water evaporated.

DISCLAIMER:

This is a factual report of the results obtained from the laboratory test of sample products. The results may be applied only to the products tested and should not be construed as applicable to other similar products of the manufacturer. The report is not a recommendation or disapprobation by VTEC Laboratories, Inc. of the material tested. While this report may be used for obtaining product acceptance, it may not be used in advertising.


Notice: VTEC Laboratories Inc. will not be liable for any loss or damage resulting from the use of the data in this report, in excess of the invoice. This report pertains to the sample tested only. Such report shall not be interpreted to be a warranty, either expressed or implied as to the suitability or fitness of said sample for such uses or applications, as the party contracting for the report may apply such sample.

Material Tested:

- 1) Manufacturer: Superior Products
- 2) Product Description: ENAMO-GRIP applied at 9 mils wet to produce 4 mils dry.
- 3) Color: White
- 4) Number of Specimens: 3
- 5) Surface: Smooth
- 6) Material description: by Manufacturer and VTEC
- 7) Date of selection: September 2004
- 9) Test Method: Water Method

Test Results:

Sample #	Sample Thickness (mils)	Weight Before (grams)	Weight After (grams)	Diameter of Exposed Surface (inches)	Exposed Surface Area (sq. ft.)	Saturation Pressure @ 90 F (in. Hg.)
1	4	239.3	239.0	3.1875	0.2217	1.42
	Relative Humidity in Chamber (RH in Decimal)	Relative Humidity in cup (RH in Decimal)	Water Vapor Transmission (grains/sq. ft. h.)	Permeance perms (grains/sq. ft. h. in. Hg.)		
	0.5	1	0.8701	1.2255		
Sample #	Sample Thickness (mils)	Weight Before (grams)	Weight After (grams)	Diameter of Exposed Surface (inches)	Exposed Surface Area (sq. ft.)	Saturation Pressure @ 90 F (in. Hg.)
2	4	244.4	244.3	3.1875	0.2217	1.42
	Relative Humidity in Chamber (RH in Decimal)	Relative Humidity in cup (RH in Decimal)	Water Vapor Transmission (grains/sq. ft. h.)	Permeance perms (grains/sq. ft. h. in. Hg.)		
	0.5	1	0.2900	0.4085		
Sample #	Sample Thickness (mils)	Weight Before (grams)	Weight After (grams)	Diameter of Exposed Surface (inches)	Exposed Surface Area (sq. ft.)	Saturation Pressure @ 90 F (in. Hg.)
3	4	240.4	240.3	3.1875	0.2217	1.42
	Relative Humidity in Chamber (RH in Decimal)	Relative Humidity in cup (RH in Decimal)	Water Vapor Transmission (grains/sq. ft. h.)	Permeance perms (grains/sq. ft. h. in. Hg.)		
	0.5	1	0.2900	0.4085		
AVERAGE PERMS:			0.6809			



Neil Schultz
Executive Director



Amirudin Rahim
Technical Director