



Thermal
Fire
Corrosion

Call us for more information at 604-576-2212

NCFR 1000 - 1X TECHNICAL DATA SHEET

CHARACTERISTICS:

- Finish**.....Satin or Clear
- Spreading Rate**.....300 sq/ft per gallon
in two (2) coats
- Drying Time @75°F & 50% R.H.**
- Between coats.....6-8 hours
- Before handling.....5 hours
- Finish should reach hardness in....48 hours
- Shipping Weight**..... .1 gallon – 10.8 lbs.
5 gallon – 51.0 lbs
- Weight/Gallon**.....9.02 +/- 0.2 lbs.

- Pacific Gravity**.....1.096
- Color**White, Clear, Custom Tinting available using
universal colorants
- Type of Cure**..... Solvent Evaporation
- Solids by weight** 60% +/- 2%
- Solids by Volume** 45% +/- 2%
- Reducer**.....Xylene
- Packaging**..... 1 & 5 gallon containers
- Shelf Life**.....1 year Unopened
- Clean up Solvent**.....Xylene

SGS/US TESTING COMPANY FIRE HAZARD CLASSIFICATION

Class A rating when tested in accordance with ASTM-84, comparable to NFPA 255, UL 723 and UBC No. 8-1

Coating Detail	Classification or Rating (When Applied to Red Oak)	
	Flame Spread	Smoke Developed
NCFR 1000 – 1X applied in two Coats at 300 sq. ft./US gal.	25	60

NOTE: Red Oak was tested based on having one of the highest burn rates of most common wood types used in building assemblies.